



**DPR Swirl 2.0      DPR Sand 1.5**  
**DPR Swirl 1.5      DPR Smooth 0.5**  
**DPR Sand 1.0**

Teifs DPR Acrylic Finishes

| Test                            | Method                         | Criteria  | Results   |
|---------------------------------|--------------------------------|---|---|
| Abrasion Resistance*            | ASTM D968                      | No cracking or loss of film integrity at 528 quarts (500 L) of sand                 | Pass @ 1000 Liters                                |
| Accelerated Weathering          | ASTM G153 (Formerly ASTM G 23) | No deleterious effects at 2000 hours when viewed under 5x magnification             | Pass  |
| Flexibility (Mandrel Bend)      | ASTM D522, Method B            | No Requirement  | 1" diameter @ -4°F                                |
| Freeze/Thaw Resistance*         | ASTM E 2485                    | No deleterious effects at 10 cycles when viewed under 5x magnification              | Pass @ 60 cycles                                  |
| Mildew Resistance*              | ASTM D 3273                    | No growth supported during 28 day exposure period                                   | Pass @ 35 days                                    |
| Mildew Resistance*              | MIL 810 B 508                  |   | No growth 28 days                                 |
| Moisture Resistance*            | ASTM D2247                     | No deleterious effects at 14 day exposure   | Pass @ 28 days                                    |
| Salt Fog Resistance*            | ASTM B117                      | No deleterious effects at 300 hours   | Pass @ 900 hrs                                    |
| Scrub Resistance                | ASTM D2486                     | No Requirement  | Pass @ 10,000 Cycles                              |
| Surface Burning Characteristics | ASTM E84                       | Individual components shall each have a flame spread <25, and smoke developed < 450 | Flame Spread: 0 to 15<br>Smoke Developed: 0 to 15 |
| Water Vapor Transmission        | ASTM E 96 Procedure B          | Vapor Permeable   | Permeable   |
| VOC                             | EPA Reference Test Method 24   | US EPA, South Coast AQMD and Greenseal Standard                                     | 8 g/L   |

\*Tested with Teifs Basecoat



DPR SWIRL 2.0



DPR SAND 1.0



DPR SWIRL 1.5



DPR SMOOTH 0.5



DPR SAND 1.5

**DESCRIPTION:**

- 100% Acrylic-based textured finish.
- DPR (Dirt Pick-up Resistance) chemistry.
- Integrally colored with high-quality pigments.
- Exceeds ASTM and ICC Acceptance Criteria.

**USES:**

- Exterior or interior finish coat over:
- Teifs Exterior Insulation and Finish Systems.
  - Properly prepared masonry, stucco, and concrete surfaces.
  - Interior application over drywall, plaster, or properly prepared masonry or concrete.

**COMPOSITION:**

- Binder base: 100% acrylic polymer with surface-hardening property.
- Aggregate: Pure crushed marble, rust-free.
- Water-based: VOC-compliant. Meets SCAQMD Rule 1113 when using Parex USA Non-VOC Colorants.
- Pigment base: Titanium dioxide
- Color: Parex USA standard colors or tinted to desired custom color.

*Note: "The Plus" Advantage can be added to any Teifs finish or coating. "The Plus" provides additional protection against mildew and algae growth.*

**CONTAINER:**

- 65 lb (29.5kg) net weight in plastic pails.
- Storage: Protect from sun and freezing at all times.
  - Do not stack pails more than 3 pails high.
  - Shelf Life: Reference Parex USA Expiration Date of Products Technical Bulletin.

**COVERAGE:**

Depending on the condition of the substrate and method of application, approximate coverages per pail are:

**Swirl 2.0**

Aggregate size: 2.0mm  
90-110 ft<sup>2</sup> (8.3-10.2 m<sup>2</sup>)

**Swirl 1.5**

Aggregate size: 1.5mm  
120-135 ft<sup>2</sup> (11-12.5 m<sup>2</sup>)

**Smooth 0.5**

Aggregate size: 0.5mm  
280-300 ft<sup>2</sup> (26-28 m<sup>2</sup>)

**Sand 1.0**

Aggregate size: 1.0mm  
150-165 ft<sup>2</sup> (14-15 m<sup>2</sup>)

**Sand 1.5**

Aggregate size: 1.5mm  
90-110 ft<sup>2</sup> (8.4-10.2 m<sup>2</sup>)

**DRYING TIME:**

24-48 hours under normal conditions. High humidity and low temperatures extend drying time.

**CLEAN-UP:**

Water-soluble prior to drying. Clean tools and containers with water prior to drying.

**SURFACE PREPARATION:**

- Remove surface contaminants such as dust or dirt without damaging the substrate.
- For previously painted surfaces, all loose and chalking paint must be removed, and glossy surfaces dulled.
- New concrete and masonry must be clean and cured a minimum of 28 days.
- Check concrete surfaces for alkalinity and treat. Any form-release agents or bond breakers must be removed.
- Uneven concrete or masonry can be leveled with any TeifsBase Basecoat & Adhesive, or other suitable, compatible product.
- For interior drywall, prepare as for painting.
- Parex USA recommends the use of primers to enhance the appearance and uniformity of the finish, improved coverage, and decrease the chance of efflorescence. This

is especially true when using dark colors or finishes with a large aggregate. If specified, prime with Parex USA Primer or Variance VariPrime Sanded, refer to Product Data Sheet.

- For additional options, contact Parex USA Technical Services Department.

**MIXING:**

- Use clean equipment for mixing and preparation.
- Stir to obtain a homogeneous consistency using a heavy-duty 1/2-in. (13mm) drill with a rust free paddle at 400-500 rpm. Avoid air entrainment.
- Add the amount of water needed to achieve finish texture. To avoid color variations, add the same amount of water to each pail of finish up to 16oz (0.5L).

**APPLICATION:**

- Read the entire label before using this product.
- Always maintain a wet edge and work to corners or joints. For best color consistency, use finish with the same batch number within a wall section. For more information, see Technical Bulletin: "Boxing Acrylic Finishes".
- Keep container closed when not in use.
- Use a clean stainless steel trowel and apply a uniform coat the thickness of the largest aggregate size of the finish.
- Texturing Swirl 2.0, Swirl 1.0, Sand 1.0, and Sand 1.5 Finishes: Use a clean plastic float or a stainless steel trowel. A plastic float will roll the large aggregates more than a stainless steel trowel. Continuously dry clean the plastic float or steel trowel while texturing. Use consistent pressure and motion to achieve the desired texture.
- Texturing Smooth 0.5 Finish:
  - Optional: Level stucco brown coats with any TeifsBase Basecoat & Adhesive and let dry prior to finish application.
  - Smooth 0.5 Finish cannot generally be floated. Texture will be "as trowelled."

- Smooth 0.5 Finish can be trowelled smooth to simulate the texture of limestone.
- For smoothest application, apply in two tight coats. Allow first coat to dry enough that it will not be disturbed during application of the second coat. When second coat is partially dry, trowel to desired smoothness. Light, consistent misting with water during smoothing will increase smoothness. Variations in color tint and smoothness should be expected.
- Spray application: To achieve consistent texture, spray application must use consistent motion, pressure, distance and spray angle. A job-site mock up for spray application is advised.

**LIMITATIONS:**

- Ambient and surface temperature must be 40°F (4°C) or higher during application and drying time. Supplemental heat and protection from precipitation must be provided as needed.
- Use only on surfaces that are sound, clean, dry, unpainted, and free from any residue that might affect the ability of the finish to bond to the surface.
- Application in direct sunlight in hot weather may adversely affect aesthetics.
- Parex USA is not responsible for color correctness after finish has been applied.

**WARNING:**

- Read complete warning information printed on product container prior to use. For medical emergency information, call 1-800-424-9300.
- For more information on handling this product refer to its Safety Data Sheet (SDS). The most current SDS and Product Data Sheet (PDS) can be found on our website.
- This Product Data Sheet has been prepared in good faith on the basis of information available at the time of publication. It is intended to provide users with information about the guidelines for the proper use and application of the covered product(s) under normal environmental and working conditions. Because each project is different, Parex USA, Inc. cannot be responsible for the consequences of variations in such conditions, or for unforeseen conditions.

Parex USA, Inc.  
4125 E. La Palma Ave., Suite 250  
Anaheim, CA 92807  
(866) 516-0061 Tech Support: (800) 226-2424



EIMA

SMA



PAREXUSA SUSTAINABILITY