


Adheez Sheathing Adhesive



DESCRIPTION:

- Adhesive to bond EPS to listed substrates
- 100% Acrylic polymer base
- Ready to use, applied without the addition of cement
- Exceptional workability

USES:

- EPS adhesive for the following substrates:
 - Wood
 - Gypsum Sheathing
 - Glass Mat Sheathing
 - Metal Siding and painted surfaces in combination with mechanical fasteners

COMPOSITION :

- Binder base: 100% acrylic polymers
- Water-based: VOC-compliant
- Color: Light gray



COVERAGE:

Depending on the condition of substrate and the method of application, approximate coverage per pail is:

 5/16 in. (8mm) notched trowel: 295-316 ft² (27-29 m²) 3/16 in. (5mm) notched trowel: 349-380 ft² (32-35 m²)

CONTAINER:

60 lbs. (27.22 kg) net weight in plastic pails.

- Storage: Protect from sun and freezing at all times
- Do not stack pails more than 3 pails high
- Shelf Life: Reference Parex USA Expiration Date of Products Technical Bulletin.

WORKING TIME:

Set time depends upon temperature and humidity. High humidity and low temperatures extend working time.

DRYING TIME:

Full adhesive bond strength is reached after 1-2 days, depending upon humidity and temperature.

CLEAN-UP:

Water-soluble prior to drying. Clean tools and containers with water prior to drying.

SURFACE PREPARATION:

- Planar irregularities are limited to 1/4 in. (6mm) or less in a 4 ft. (1.22 m) radius.
 Surface irregularities are limited to 1/4 in. (6mm) or less.
- Irregular and uneven surface should be filled with any Teifs Basecoat & Adhesive

- Remove surface contaminants such as dust or dirt without damaging the substrate.
- Painted substrates must have paint removed with methods that result in no more than 10 percent of the remaining surface having paint.
- For additional options for surface preparation, contact Parex USA Technical Services Department.

MIXING:

- Use clean equipment for mixing and preparation.
- Teifs Adheez is a factory pre-mixed product. Thoroughly stir Adheez prior to use, avoiding air entrainment
- Up to 16 oz. (0.47 L) of cool potable water may be added to Adheez to improve workability.
- Only Parex USA approved additives can be added to this product.
- Keep container closed when not in use.

APPLICATION:

- Read the entire label before using this product.
- Adhesive Application: Apply the adhesive to the entire surface on one face of the insulation board, using a 5/16 in. (8mm) or 3/16 in. (5mm) notched trowel.
- The ribbons should be of uniform thickness, run vertically and reach the perimeter of the insulation board. To ensure high initial grab and uniform adhesive contact, apply insulation board to wall with firm pressure to entire surface. Apply sufficient pressure to flatten adhesive ridges

LIMITATIONS:

- Ambient and surface temperatures must be 40 °F (4°C) or higher during application and drying time. Supplemental heat and protection from precipitation must be provided as needed.
- Use only on surfaces that are sound, clean, dry, unpainted, and free from any residue that might affect the ability of Teifs Adheez to bond to the surface.
- Avoid application in direct sunlight in hot weather.

WARNING:

- Read complete warning information printed on product container prior to use. For medical emergency information, call 1-800-424-9300.
- For more information on handling this product refer to its Safety Data Sheet (SDS). The most current SDS and Product Data Sheet (PDS) can be found on our website.
- This Product Data Sheet has been prepared in good faith on the basis of information available at the time of publication. It is intended to provide users with information about the guidelines for the proper use and application of the covered product(s) under normal environmental and working conditions. Because each project is different, Parex USA, Inc. cannot be responsible for the consequences of variations in such conditions, or for unforeseen conditions.

Parex USA, Inc. 4125 E. La Palma Ave., Suite 250 Anaheim, CA 92807 (866) 516-0061 Tech Support: (800) 226-2424



Facilities French Camp, CA North Hollywood, CA Riverside, CA San Diego, CA Colorado Springs, CO Haines City, FL Duluth, GA Redan, GA Albuquerque, NM Allentown, PA San Antonio, TX